QC ABSTRACT

NAME OF WORK: Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	Block(400*150*200)	BLOCK DENSITY	One Test		1	1
		WATER ABSORPTION	One Test		1	1
		DIMENSION ANALYSIS	One Test		1	1
		COMPRESSIVE STRENGTH	One Test		1	1
6	Precast (100mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
7	Precast (250mm)	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive Strength	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
8	PCC(M15)	Compressive Strength(7days and 28days)	5 set /51-100 cum	73.1	10	10

Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore-97

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-11-25-57** **Date: 30-07-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division
Agency	:	Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97
Customer's Reference	:	BBMP/EEE/BTP/WO/ 56 /2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	27-07-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	28-07-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.22	–
2	Finess by Air permeablity method (m^2/kg,Min)	289.5	225m^2/kg, Min
3	Density (gm/cc)	3.11	–
4	Standard Consistency (%)	27.5%	Not specified
5	Initial Setting time	170 minutes	Not less than 30 minutes
6	Final Setting time	260 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2020-11-25-57** **Date: 25-08-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division
Agency	:	Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97
Customer's Reference	:	BBMP/EEE/BTP/WO/ 56 /2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	27-07-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	28-07-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	29.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	38.5N/mm^2	Not less than 37 N/mm^2
3	28 Days	56.5N/mm^2	Not less than 53 N/mm^2

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

Assistant Executive Engineer
Vidyaranyapura Sub Division
BBMP, Bangalore-97

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-11-25-57** **Date: 30-07-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division
Agency	:	Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97
Customer's Reference	:	BBMP/EEE/BTP/WO/ 56 /2020-21
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	27-07-20
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	27-07-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	242	242	1.6	98.4	90-100
3	20 mm	7152	7394	49.3	50.7	30-70
4	10 mm	3885	11279	75.2	24.8	10-35
5	4.75 mm	3205	14484	96.6	3.4	0-5
6	Pan	516	15000	100.0	0	---

CIVIL PRO Sig. Date. BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-11-25-57** **Date: 30-07-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	10.9	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.6	
3	Specific Gravity	2.63	_
4	Bulk Density(Loose) (Kg/l)	1.43	_
5	Bulk Density(Compacted) (Kg/l)	1.48	_
6	Water Absorption(%)	0.18	_

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2020-11-25-57** **Date: 29-07-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division
Agency	:	Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97
Customer Reference	:	BBMP/EEE/BTP/WO/ 56 /2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	27-07-20
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	27-07-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	272	272	5.4	94.6	90-100
3	10 mm	2758	3030	60.6	39.4	25-55
4	4.75 mm	1759	4789	95.8	4.2	0-10
5	Pan	211	5000	100	0	–

CIVIL Pro Sig. Date. BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2020-11-25-57** **Date: 29-07-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	10.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	9.6	
3	Specific Gravity	2.63	_
4	Bulk Density(Loose) (Kg/l)	1.45	_
5	Bulk Density(Compacted) (Kg/l)	1.51	_
6	Water Absorption(%)	0.22	_
7	Aggregate crushing Value(%)	22.2	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	22.9	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signature
Quality Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-11-25-57** **Date: 29-07-20**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 27-07-20

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 27-07-20

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	86	86	8.6	91.4	90-100	90-100	90-100	95-100
3	2.36 mm	145	231	23.1	76.9	60-95	75-100	85-100	95-100
4	1.18 mm	156	387	38.7	61.3	30-70	55-90	75-100	90-100
5	600 micron	188	575	57.5	42.5	15-34	35-59	60-79	80-100
6	300 micron	175	750	75.0	25.0	5-20	8-30	12-40	15-50
7	150 micron	162	912	91.2	8.8	0-10	0-10	0-10	0-15
8	Pan	88	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

CIVIL Pro Sig..... Date..... BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2020-11-25-57** **Date: 29-07-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	2.4	_
2	Specific Gravity	2.59	_
3	Material finer than 75 micron(%)	7.3	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT ON PHYSICAL REQUIREMENTS OF SOLID CONCRETE BLOCKS

Lab ID	:	**CP-2020-11-25-57** **Date: 08-08-20**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division
Agency	:	Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97
Customer's Reference	:	BBMP/EEE/BTP/WO/ 56 /2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	05-08-20
Sample Type/Size	:	Solid concrete blocks size (400X150X200)mm
Reference to BIS codes	:	IS : 2185 (Part 1) : 2005(RA 2010) Concrete Masonry Specification Part 1:Hollow and Solid Concrete Blocks (Dimensions -Annex-B, Clause 9.2 and 10 , Block density Annex -C Clause 9.3 and10, Compressive strength Annex -D Clause 9.4 and 10, Water absorption Annex -E Clause 9.5 and 10)
Date of test	:	05-08-20

BLOCK DENSITY:

Sl. No.	Measurement of overall Dimensions of Individual Blocks			Overall Volume of the Block in Cubic Centimetres	Weight of Oven Dried Block in Kilograms to the nearest 10 Gram	Block Density in Kg/cum*10^6	Avg.Block Density in (Kg/cum)	As per IS 2185(Part 1) :2005 (RA 2010)
	Length	Breadth	Height					
	mm	mm	mm	(Cm^3)	Kg	Kg/m^3	Kg/m^3	
1	405	149	202	12190	32.892	2698.3	2724.9	Not less than 1800Kg/m^3
2	402	150	203	12241	33.840	2764.5		
3	398	150	202	12059	32.704	2711.9		

WATER ABSORPTION:

Sl. No.	Wet weight after water absorption	Dry weight (Oven dry)	Water Absorption	Avg.Water Absorption	As per IS 2185(Part 1):2005 (RA 2010)
	kg	kg	%	%	
1	33.91	32.25	4.89	4.25	Shall not be more than 10% by mass
2	33.57	32.14	4.28		
3	33.44	32.24	3.59		

CIVIL PRO Sig. Date. BANGALORE

Lab ID : **CP-2020-11-25-57** **Date: 08-08-20**

DIMENSION ANALYSIS

Sl.no	Length mm	Breadth mm	Height mm	Requirement as per IS 2185(Part 1):2005
1	401	149	201	Length : ± 5mm Breadth : ± 3mm Height : ± 3mm
2	400	151	202	
3	401	151	200	
4	401	152	200	
5	404	152	202	
6	403	153	201	
7	400	151	203	
8	399	150	201	
9	399	150	201	
10	399	151	203	
11	401	153	202	
12	402	151	201	
13	403	151	199	
14	402	150	202	
15	400	151	199	
16	403	151	201	
17	404	153	202	
18	399	152	202	
19	400	151	199	
20	402	149	202	
Average of 20	**401**	**151**	**201**	

CIVIL Pro Sig Date BANGALORE

Lab ID : **CP-2020-11-25-57** **Date: 08-08-20**

COMPRESSIVE STRENGTH:

Sl. No.	Size of solid block		Area	Failure Load	Compressive strength	Average Compressive strength
	Length	Breadth				
	mm	mm	(mm^2)	(KN)	N/mm^2	(N/mm^2)
1	400	149	59708	273.0	4.6	4.5
2	400	151	60480	272.6	4.5	
3	401	151	60659	277.0	4.6	
4	401	152	60960	280.3	4.6	
5	404	152	61348	278.1	4.5	
6	403	153	61615	276.8	4.5	
7	400	151	60458	274.8	4.5	
8	399	150	60067	272.7	4.5	

As per IS Requirements (Table 2, Clause 5.1, 5.2 and 9.4)

Compressive strength		
Grade	**Minimum average**	**Minimum Individual units.**
C (5.0)	5.00 N/mm^2	4.00 N/mm^2
C (4.0)	4.00 N/mm^2	3.20 N/mm^2

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID : **CP-2020-11-25-57** **Date: 17-08-20**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 11-08-20

Sample Type /Size : Precast Cover Slab (100mm)

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 11/08/2020

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.51	100.48	1.116	4477	80.9	18.1	16.8	21.0
2	Cover Slab-2	75.49	100.52	1.122	4475	82.3	18.4	17.1	21.4
3	Cover Slab-3	75.50	100.51	1.118	4476	81.5	18.2	16.9	21.2

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL PRO Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID : **CP-2020-11-25-57** **Date: 15-08-20**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 11-08-20

Sample Type /Size : Precast Cover Slab (250mm)

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 11/08/2020

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	200.51	250.48	3.116	31570	230.9	7.3	6.8	8.5
2	Cover Slab-2	200.49	250.52	3.122	31564	232.3	7.4	6.8	8.6
3	Cover Slab-3	200.50	250.51	3.118	31567	231.5	7.3	6.8	8.5

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 10/08/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-08-20

Customer ID : Culvert Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 10/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvert Copping Concrete	M15	03/08/2020	10/08/2020	151.62 X 149.57 X 151.93	22678	**8.925**	289.3	12.8	12.5
2	Culvert Copping Concrete	M15	03/08/2020	10/08/2020	151.91 X 151.40 X 149.53	22999	**8.595**	285.2	12.4	
3	Culvert Copping Concrete	M15	03/08/2020	10/08/2020	150.23 X 149.28 X 151.10	22426	**8.204**	278.9	12.4	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 31/08/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 05-08-20

Customer ID : Culvert Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 31/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Culvert Copping Concrete	M15	03/08/2020	31/08/2020	151.54 X 149.52 X 151.83	22659	**8.811**	385.9	17.0	17.5
2	Culvert Copping Concrete	M15	03/08/2020	31/08/2020	150.73 X 149.70 X 151.07	22564	**8.811**	402.3	17.8	
3	Culvert Copping Concrete	M15	03/08/2020	31/08/2020	151.74 X 151.09 X 149.93	22926	**8.830**	402.7	17.6	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 13/08/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-08-20

Customer ID : Vent Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Vent Concrete	M15	06/08/2020	13/08/2020	149.30 X 151.77 X 151.40	22659	**8.925**	273.2	12.1	12.2
2	Vent Concrete	M15	06/08/2020	13/08/2020	149.53 X 149.75 X 150.75	22391	**8.595**	272.0	12.1	
3	Vent Concrete	M15	06/08/2020	13/08/2020	149.45 X 151.29 X 151.85	22609	**8.204**	278.7	12.3	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 03/09/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-08-20

Customer ID : Vent Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Vent Concrete	M15	06/08/2020	03/09/2020	150.64 X 151.94 X 150.55	22889	**8.811**	402.1	17.6	17.7
2	Vent Concrete	M15	06/08/2020	03/09/2020	150.97 X 151.73 X 150.59	22908	**8.811**	402.8	17.6	
3	Vent Concrete	M15	06/08/2020	03/09/2020	149.87 X 149.65 X 149.48	22427	**8.830**	401.4	17.9	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 13/08/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-08-20

Customer ID : Vent Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 13/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Vent Concrete	M15	06/08/2020	13/08/2020	149.26 X 151.63 X 150.94	22633	**8.925**	290.0	12.8	12.5
2	Vent Concrete	M15	06/08/2020	13/08/2020	150.08 X 149.13 X 151.42	22381	**8.595**	273.2	12.2	
3	Vent Concrete	M15	06/08/2020	13/08/2020	151.67 X 150.07 X 149.33	22761	**8.204**	281.1	12.3	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 03/09/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 08-08-20

Customer ID : Vent Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Vent Concrete	M15	06/08/2020	03/09/2020	150.31 X 151.29 X 151.46	22740	**8.811**	405.4	17.8	17.6
2	Vent Concrete	M15	06/08/2020	03/09/2020	151.39 X 150.54 X 150.90	22790	**8.811**	392.1	17.2	
3	Vent Concrete	M15	06/08/2020	03/09/2020	151.78 X 150.18 X 151.58	22795	**8.830**	404.7	17.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 17/08/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 12-08-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 17/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	10/08/2020	17/08/2020	150.41 X 151.06 X 149.29	22721	**8.925**	277.5	12.2	12.4
2	Copping Concrete	M15	10/08/2020	17/08/2020	151.86 X 149.73 X 149.80	22738	**8.595**	279.1	12.3	
3	Copping Concrete	M15	10/08/2020	17/08/2020	150.99 X 150.02 X 150.61	22652	**8.204**	290.3	12.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 07/09/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 12-08-20

Customer ID : Copping Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 07/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Copping Concrete	M15	10/08/2020	07/09/2020	149.04 X 151.47 X 151.02	22575	**8.811**	400.9	17.8	17.5
2	Copping Concrete	M15	10/08/2020	07/09/2020	149.54 X 150.16 X 151.77	22455	**8.811**	384.3	17.1	
3	Copping Concrete	M15	10/08/2020	07/09/2020	150.57 X 151.08 X 151.32	22748	**8.830**	401.0	17.6	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 21/08/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-08-20

Customer ID : Ramp Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 21/08/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Ramp Concrete	M15	14/08/2020	21/08/2020	149.51 X 151.04 X 151.77	22583	**8.925**	286.2	12.7	12.6
2	Ramp Concrete	M15	14/08/2020	21/08/2020	150.36 X 151.47 X 150.24	22774	**8.595**	290.5	12.8	
3	Ramp Concrete	M15	14/08/2020	21/08/2020	151.44 X 149.18 X 149.86	22592	**8.204**	282.4	12.5	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2020-11-25-57** **Date: 11/09/2020**

Customer : Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.

Address : Vidyaranyapura Sub Division, BBMP, Bangalore.

Project Name : Improvements Roads and Drains and Providing Covering Slabs at M S Palya Gramthana Ganesh Layout M S Palya Extension and Surrounding Areas in Ward No 11 Kuvempunagara in Vidyaranyapura Sub Division

Agency : Sri. Abbu Sambasiva Reddy, No:1BS, Sree Arcade Layout, 4th Block Doddabommasandra, Vidyaranyapura Post, Bangalore-97

Customer's Reference : BBMP/EEE/BTP/WO/ 56 /2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-08-20

Customer ID : Ramp Concrete

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 11/09/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	Ramp Concrete	M15	14/08/2020	11/09/2020	151.28 X 149.28 X 150.26	22584	**8.811**	388.7	17.2	17.5
2	Ramp Concrete	M15	14/08/2020	11/09/2020	149.90 X 150.15 X 150.20	22508	**8.811**	400.6	17.8	
3	Ramp Concrete	M15	14/08/2020	11/09/2020	149.80 X 150.94 X 149.62	22611	**8.830**	397.1	17.6	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL PRO Sig. Date. BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****